

## Technical Data Sheet

# HAC5015G

## PC/ABS

### PRODUCT DESCRIPTION:

PC/ABSHAC5015G is a good dimensional stability PC/ABS resin with 15% glass fiber reinforced.

### FEATURES:

- **High Modulus**
- good dimensional stability

### APPLICATION:

- **Sunroof ring**
- glove box

Properties	Standard	Condition	Unit	Typical Value
<b>Physical</b>				
Density	ISO 1183	23°C	g/cm <sup>3</sup>	1.24
Mold Shrinkage	ISO 294	23°C, 48hr	%	0.2-0.4
<b>Mechanical</b>				
Tensile Strength at Yield	ISO 527	5mm/min	MPa	73
Flexural Strength	ISO 178	2mm/min	MPa	115
Flexural Modulus	ISO 178	2mm/min	MPa	4050
Notched Charpy Impact	ISO 179	4J, 23°C	kJ/m <sup>2</sup>	8.6
Unnotched Charpy Impact	ISO 179	4J, 23°C	kJ/m <sup>2</sup>	26
<b>Thermal</b>				
Heat Deflection Temperature	ISO 75	120°C/hr, 1.80MPa	°C	120
Vicat Softening Temperature	ISO 306	50°C/hr, 5kg	°C	130
<b>Other Properties</b>				
Flammability	ISO 3795	355×100×3 mm	mm/min	≤80

Processing Parameters		Value	Unit
<b>Pre-treatment</b>			
Drying Temperature		110-120	°C
Drying Time		4-6	hour
Maximum Moisture Content		0.02	%
<b>General Guidelines</b>			
Barrel Temperature	Rear	220-240	°C
	Middle	240-260	°C
	Front	270-280	°C
Nozzle		260-270	°C
Melt Temperature		270-280	°C
Mold Temperature		60-80	°C

**Note :**

1. Values are measured at 23°C and in RH of 50% on injection molded specimens.
2. Typical values for uncolored products, not specifications, and may vary slightly with different colors.
3. Flexural strength is tested with fixed deflection.
4. HDT: specimens are unannealed.
5. The general guidelines are only for reference. Exact settings have to follow the product and machine conditions.

**Disclaimer :**

To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the data compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or process described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. You may not copy this document to a web site.

Kumho-Sunny expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication.